

Name:  
Enrolment No:



## UNIVERSITY OF PETROLEUM AND ENERGY STUDIES

**End Semester Examination, December 2023**

**Program Name : B.Tech (CE+RP)**  
**Course Name : Corrosion Engineering**  
**Course Code : CHCE3025P**  
**Nos. of page(s) : 2**

**Semester: VII**  
**Time: 03 hrs.**  
**Max. Marks: 100**

**Instructions:** *The question paper consists of two sections. Answer the questions section wise in the answer booklet. Note: Assume suitable data wherever necessary*

### SECTION-A (Answer all questions)

S. No.		Marks	CO
Q1	Criticize corrosion in water and aqueous solutions.	10	CO4
Q2	Discuss about galvanic corrosion, microbiologically induced corrosion, pitting corrosion, erosion corrosion, stress corrosion cracking and their preventions.	10	CO1
Q3	Describe corrosion and justify how the corrosion rate of a metal/alloy varies with different environments.	10	CO1
Q4	Determine whether iron is stable in aqueous solution at pH = 3, 5, and 7. Plot the driving EMF and the Gibbs free-energy as a function of pH. Assume $P_{H_2} = 1$ atm. and $[Fe^{2+}] = 10^{-6}$ M.	10	CO2
Q5	Illustrate stainless steel alloys and its corrosion behavior.	10	CO4
Q6	A new heat exchanger is required in conjunction with a rearrangement of existing facilities. Because of corrosion, the expected life of a carbon steel heat exchanger is 5 years. The installed cost is \$9500. An alternative to the heat exchanger is a unit fabricated of AISI type 316 stainless steel, with an Installed cost of \$26,500 and an estimated life of 15 years, to be written off in 11 years. The minimum acceptable interest rate is 10 percent, the tax rate is 48 percent, and the depreciation method is straight line. <b>Justify</b> which unit would be more economical based on annual costs.	10	CO5

### SECTION-B (Answer all questions)

Q7	<p>Construct an Evans diagram (E vs. log i) for the corrosion of silver in a hydrogen saturated 0.1M HCl solution where the activity of <math>Ag^+</math> is <math>10^{-18}</math>M. The corrosion reaction data is as follows:</p> <p style="text-align: center;"><math>[Ag^+] = 10^{-18}</math> M, <math>[H^+] = 0.1</math> M</p> <p style="text-align: center;">Tafel slopes: <math>\beta_a = 0.1</math> V/decade, <math>\beta_b = -0.1</math> V/decade</p> <p style="text-align: center;">Tafel constant: <math>a_c = -0.0824</math> V vs SHE (cathode)</p> <p style="text-align: center;">Exchange current densities: <math>i_{Ag}^o = 0.8 \frac{A}{cm^2}</math>, <math>i_{H_2}^o = 0.15 \frac{A}{cm^2}</math></p> <p>Calculate:</p> <p>(a) Equilibrium potentials of the hydrogen and Ag redox reaction.</p> <p>(b) Corrosion current and corrosion potential.</p>	20	CO2
----	--	----	-----

	(c) Protection current to prevent corrosion.		
Q8	Describe in detail about cathodic and anodic protection methods and explain with Evans diagram.	20	CO3

**Table: Standard Electrode Potentials at 25 °C and Their Isothermal Temperature Coefficients**

Electrode Reaction	$e^o$ (V vs SHE)	$\left(\frac{dE^o}{dT}\right) \times 10^3 \left(\frac{V}{oC}\right)$	
Li <sup>+</sup>  Li	Li <sup>+</sup> + e <sup>-</sup> = Li	-3.045	-0.534
Rb <sup>+</sup>  Rb	Rb <sup>+</sup> + e <sup>-</sup> = Rb	-2.925	-1.245
Cs <sup>+</sup>  Cs	Cs <sup>+</sup> + e <sup>-</sup> = Cs	-2.923	-1.197
K <sup>+</sup>  K	K <sup>+</sup> + e <sup>-</sup> = K	-2.925	-1.080
Ra <sup>2+</sup>  Ra	Ra <sup>2+</sup> + 2e <sup>-</sup> = Ra	-2.916	-0.59
Ba <sup>2+</sup>  Ba	Ba <sup>2+</sup> + 2e <sup>-</sup> = Ba	-2.906	-0.395
Ca <sup>2+</sup>  Ca	Ca <sup>2+</sup> + 2e <sup>-</sup> = Ca	-2.866	-0.175
Na <sup>+</sup>  Na	Na <sup>+</sup> + e <sup>-</sup> = Na	-2.714	-0.772
La <sup>3+</sup>  La	La <sup>3+</sup> + 3e <sup>-</sup> = La	-2.522	+0.085
Mg <sup>2+</sup>  Mg	Mg <sup>2+</sup> + 2e <sup>-</sup> = Mg	-2.363	+0.103
Be <sup>2+</sup>  Be	Be <sup>2+</sup> + 2e <sup>-</sup> = Be	-1.847	+0.565
Al <sup>3+</sup>  Al	Al <sup>3+</sup> + 3e <sup>-</sup> = Al	-1.662	+0.504
Ti <sup>2+</sup>  Ti	Ti <sup>2+</sup> + 2e <sup>-</sup> = Ti	-1.628	-
Zr <sup>4+</sup>  Zr	Zr <sup>4+</sup> + 4e <sup>-</sup> = Zr	-1.529	-
V <sup>2+</sup>  V	V <sup>2+</sup> + 2e <sup>-</sup> = V	-1.186	-
Mn <sup>2+</sup>  Mn	Mn <sup>2+</sup> + 2e <sup>-</sup> = Mn	-1.180	-0.08
Zn <sup>2+</sup>  Zn	Zn <sup>2+</sup> + 2e <sup>-</sup> = Zn	-0.762	+0.09
Cr <sup>3+</sup>  Cr	Cr <sup>3+</sup> + 3e <sup>-</sup> = Cr	-0.744	+0.468
SbO <sub>2</sub> <sup>-</sup>  Sb	SbO <sub>2</sub> <sup>-</sup> + 2H <sub>2</sub> O + 3e <sup>-</sup> = Sb + 4OH <sup>-</sup>	-0.670	-
Ga <sup>3+</sup>  Ga	Ga <sup>3+</sup> + 3e <sup>-</sup> = Ga	-0.529	+0.67
S <sup>2-</sup>  S	S + 2e <sup>-</sup> = S <sup>2-</sup>	-0.510	-
Fe <sup>2+</sup>  Fe	Fe <sup>2+</sup> + 2e <sup>-</sup> = Fe	-0.440	+0.052
Cr <sup>3+</sup> , Cr <sup>2+</sup>  Pt	Cr <sup>3+</sup> + e <sup>-</sup> = Cr <sup>2+</sup>	-0.408	-
Cd <sup>2+</sup>  Cd	Cd <sup>2+</sup> + 2e <sup>-</sup> = Cd	-0.402	-0.093
Ti <sup>3+</sup> , Ti <sup>2+</sup>  Pt	Ti <sup>3+</sup> + e <sup>-</sup> = Ti <sup>2+</sup>	-0.369	-
Tl <sup>+</sup>  Tl	Tl <sup>+</sup> + e <sup>-</sup> = Tl	-0.336	-1.327
Co <sup>2+</sup>  Co	Co <sup>2+</sup> + 2e <sup>-</sup> = Co	-0.277	+0.06
Ni <sup>2+</sup>  Ni	Ni <sup>2+</sup> + 2e <sup>-</sup> = Ni	-0.250	+0.06
Mo <sup>3+</sup>  Mo	Mo <sup>3+</sup> + 3e <sup>-</sup> = Mo	-0.20	-
Sn <sup>2+</sup>  Sn	Sn <sup>2+</sup> + 2e <sup>-</sup> = Sn	-0.138	-0.282
Pb <sup>2+</sup>  Pb	Pb <sup>2+</sup> + 2e <sup>-</sup> = Pb	-0.126	-0.451
Ti <sup>4+</sup> , Ti <sup>3+</sup>  Pt	Ti <sup>4+</sup> + e <sup>-</sup> = Ti <sup>3+</sup>	-0.040	-
H <sup>+</sup> , H <sub>2</sub>  Pt	H <sup>+</sup> + e <sup>-</sup> = 1/2 H <sub>2</sub>	T0.000	T0.000
Sn <sup>4+</sup> , Sn <sup>2+</sup>  Pt	Sn <sup>4+</sup> + 2e <sup>-</sup> = Sn <sup>2+</sup>	+ 0.015	-
Cu <sup>2+</sup> , Cu <sup>+</sup>  Pt	Cu <sup>2+</sup> + e <sup>-</sup> = Cu <sup>+</sup>	+ 0.153	+0.073
Ag <sup>+</sup>  Ag	Ag <sup>+</sup> + e <sup>-</sup> = Ag	+0.799	-
Cu <sup>2+</sup>  Cu	Cu <sup>2+</sup> + 2e <sup>-</sup> = Cu	+0.337	+0.008
Fe(CN) <sub>6</sub> <sup>3-</sup> , Fe(CN) <sub>6</sub> <sup>4-</sup>  Pt	Fe(CN) <sub>6</sub> <sup>3-</sup> + e <sup>-</sup> = Fe(CN) <sub>6</sub> <sup>4-</sup>	+0.360	-
OH <sup>-</sup> , O <sub>2</sub>  Pt	1/2 O <sub>2</sub> + H <sub>2</sub> O + 2e <sup>-</sup> = 2OH <sup>-</sup>	+0.401	-0.440
Cu <sup>+</sup>  Cu	Cu <sup>+</sup> + e <sup>-</sup> = Cu	+0.521	-0.058
I <sup>-</sup>  I <sub>2</sub> , Pt	I <sub>2</sub> + 2e <sup>-</sup> = 2I <sup>-</sup>	+0.535	-0.148
MnO <sub>4</sub> <sup>-</sup> , MnO <sub>4</sub> <sup>2-</sup>  Pt	MnO <sub>4</sub> <sup>-</sup> + e <sup>-</sup> = MnO <sub>4</sub> <sup>2-</sup>	+0.564	-